



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09K 3/14, C09G 1/02, H01L 21/321		A1	(11) International Publication Number: WO 99/32570
			(43) International Publication Date: 1 July 1999 (01.07.99)
(21) International Application Number: PCT/SE98/02370 (22) International Filing Date: 18 December 1998 (18.12.98) (30) Priority Data: 60/071,291 23 December 1997 (23.12.97) US 09/009,919 21 January 1998 (21.01.98) US (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL). (71) Applicant (for SE only): EKA CHEMICALS AB [SE/SE]; S-445 80 Bohus (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): BERGÖÖ, Peter [SE/US]; 3624 Rittenhouse Course, Marietta, GA 30062 (US). LARSSON, Kenneth, Olof [SE/SE]; Kopparslagaregatan 25, S-412 61 Göteborg (SE). TOKARZ, Bozena [SE/SE]; Håkansgatan 4, S-442 39 Kungälv (SE). (74) Agent: NYANDER, Johan; Eka Chemicals AB, Patent Dept., P.O. Box 11556, S-100 61 Stockholm (SE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: A COMPOSITION FOR CHEMICAL MECHANICAL POLISHING			
(57) Abstract			
<p>Use of a complexing agent in a composition comprising amorphous silica for chemical mechanical polishing of a semiconductor substrate, for the purpose of avoiding metal contamination of said semiconductor substrate. A composition for chemical mechanical polishing of semiconductor substrates, which composition contains amorphous silica, ammonium ions, and a sequestering agent, and a method in which such a composition is used to polish a semiconductor substrate.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A COMPOSITION FOR CHEMICAL MECHANICAL POLISHING

The present invention relates to the use of a complexing agent in a composition for chemical mechanical polishing of a semiconductor substrate, a composition for such
5 chemical mechanical polishing, and a method in which the composition is used.

In the present application the concept of "chemical mechanical polishing", below abbreviated to "polishing" refers - except where otherwise explicitly or implicitly indicated - in addition to polishing processes performed on the semiconductor substrates at the initial phase of the semiconductor wafer production process, also to technically similar
10 processes such as chemical mechanical planarization, which is abbreviated to "planarization" below.

In the present context a "semiconductor" means - except where otherwise explicitly or implicitly indicated - a substance having semiconducting properties as well as a semiconductor component.

Polishing of semiconductor substrates using silica in combination with ammonium is disclosed in e.g. US-A-3,715,842. The silica used has preferably a particle size of less than 100 nm. The polishing composition may contain ammonium, which is referred to as an additional polishing agent. NH_4OH may be present; its contribution to the alkalinity of the silica slurry is briefly discussed. Apart from this the ammonium ions and the
20 NH_4OH are not suggested to have any particular purpose or impact on the polishing process.

The production of semiconductor wafers demands very low impurity levels. In particular metal impurities in the semiconductor substrates may be completely devastating to the substrate. Conventionally this problem has been avoided by using amorphous
25 silica particles having very low metal impurity levels. However, such high purity amorphous silicas have the drawback of being very expensive. It would be desirable to be able to use silica of cheaper grades without running the risk of contaminating the semiconductor substrate.

The problem to be solved is thus to provide a way to perform polishing on a
30 semiconductor substrate using a amorphous silica-containing composition that may hold a relatively high amount of metals while reducing or avoiding contamination of the semiconductor substrate.

This problem has now been solved by means of the present invention as defined by the appended claims. More particularly the present invention involves the use of a
35 complexing agent in a composition comprising amorphous silica for polishing of a semi-

conductor substrate, for the purpose of avoiding metal contamination of said semiconductor substrate, whereby the preferred complexing agent is NH_4OH .

The present invention also relates to a composition for polishing of semiconductor substrates, which composition contains amorphous silica, ammonium ions, and a specific type of complexing agent, namely a sequestering agent, preferably a chelating agent. A sequestering agent is a substance that removes a metal ion from a solution system by forming a complex ion that does not have the chemical reactions of the ion that is removed, and a chelating agent is an organic compound in which atoms form more than one co-ordinate bond with metals in solution.

10 The chelating agent preferably comprises a plurality of substituted acetic acid groups, and may e.g. be chosen from a group comprising ethylenediaminetetraacetic acid (EDTA), diethylenetriaminepentaacetic acid (DTPA), N-(hydroxoethyl)ethylenediamintriacetic acid (HEDTA), and nitrilo triacetic acid (NTA), or a combination thereof.

15 The amorphous silica is preferably colloidal, i.e. present in a stable dispersion or sol of discrete particles of amorphous silica; this definition is the same as put forward in "The Chemistry of Silica" by Ralph K. Iler, page 312, Wiley & Sons 1979. Preferably, the sizes of the silica particles are less than 200 nm, and suitably within the range from about 5-150 nm.

Furthermore, the present invention relates to a method for polishing of a semiconductor substrate in which a composition containing amorphous silica, ammonium ions, and a sequestering agent, preferably a chelating agent, is used. Again, the chelating agent preferably comprises a plurality of substituted acetic acid groups, and may e.g. be chosen from a group comprising ethylenediaminetetraacetic acid (EDTA), diethylenetriaminepentaacetic acid (DTPA), N-(hydroxoethyl)ethylenediamintriacetic acid (HEDTA), and nitrilo triacetic acid (NTA), or a combination thereof.

20 According to a specific embodiment of the present invention the method is a method for planarization, which is a process that shows many similarities with polishing, in the more limited scope of that term. The main differences between the methods in fact relate to their purposes, their position in the overall semiconductor wafer production process, and accordingly to the differences between the worked objects: The purpose of the polishing is to prepare the semiconductor substrate for the semiconductor wafer production process by providing it with a suitable surface for that process, whereas the object of the planarization is to accomplish a planarized surface to accommodate further processing. Evidently the polishing takes place prior to the actual semiconductor wafer production process, whereas the planarization occurs during the same. This implies that the workpiece of the polishing is a basically pure semiconductor substrate, whereas the

workpiece of the planarization is a semiconductor substrate with various layers applied upon. The substrate in the planarization may for instance be a silicon substrate with a layer of silicon dioxide on top, whereby one of the main purposes of the planarization is to remove the oxide layer.

- 5 The semiconductor substrate may contain any semiconducting substance. Preferably, the semiconducting substance in the substrate is Si, GaAs, InP, Ge, or a combination thereof.

The present invention will now be illustrated by means of a non-limiting example.

- 10 Example: A P-doped silicon wafer having a diameter of 200 mm was mounted and held in a polishing head. The polishing head was pushed down onto a polishing pad with a pressure of 0.8 psi. During the polishing, the head and the pad were rotated in opposite directions, the head at a rotating speed of approximately 60 rpm, and the pad at 60 rpm. A composition according to the invention was added as a polishing slurry onto the pad
- 15 while rotating, containing an ammonium-stabilised silica sol, Nyacol[®] 601 in an amount of 0.5 percentage by weight, calculated on the composition, and a EDTA in an amount of 7 ppm. Then the wafer was submitted to a standard cleaning procedure in which it was stripped of native oxides in a HF bath, rinsed with deionized water,
- 20 submerged in a heated and megasonic agitated cleaning bath containing deionized water, hydrogen peroxide, and ammonium hydroxide in a relation of 5:1:1, rinsed with deionized water, then submerged in a heated and megasonic agitated cleaning bath containing a very dilute solution of hydrogen chloride in deionized water, and finally rinsed with deionized water. As a reference, another silicon wafer of the same kind was polished under the same conditions and cleaning procedure, except that the ammonium-
- 25 stabilised silica sol was of a high purity grade, Glanzox 3900, and that no EDTA was added to the polishing slurry. After the polishing, the wafer surfaces were analysed by means of Total X-ray Fluorescence (TXRF) and Vapor Phase Decomposition (VPD) + Inductive Coupled Plasma with Mass Spectroscopy (ICP/MS) with respect to a number of metals, indicated in the table below. The figures in the table, which relate to presence of
- 30 metals in the silicon wafer surface after the polishing, are given as the number of atoms/cm²

Metal	Metal content in the wafer surface after polishing according to the invention	Metal content in the reference wafer surface after polishing
Ti	$0.6 \cdot 10^{10}$	$0.7 \cdot 10^{10}$
Cr	$<0.2 \cdot 10^{10}$	$2 \cdot 10^{10}$
Fe	$0.5 \cdot 10^{10}$	$1 \cdot 10^{10}$
Ni	$1 \cdot 10^{10}$	$2 \cdot 10^{10}$
Cu	$5 \cdot 10^{10}$	$9 \cdot 10^{10}$
Al	$0.4 \cdot 10^{10}$	$2 \cdot 10^{10}$
Na	$6 \cdot 10^{10}$	$8 \cdot 10^{10}$

Evidently, metal contamination of the wafer surface as polished is clearly lessened by the present invention.

5

1. Use of a complexing agent in a composition comprising amorphous silica for chemical mechanical polishing of a semiconductor substrate, for the purpose of avoiding
5 metal contamination of said semiconductor substrate.

2. Use according to claim 2, characterised in that the complexing agent is NH_4OH .

10 3. A composition for chemical mechanical polishing of semiconductor substrates, which composition contains amorphous silica and ammonium ions, characterised in that the composition comprises a sequestering agent.

4. A composition according to claim 3, characterised in that the sequestering agent is a chelating agent.
15

5. A composition according to claim 4, characterised in that the chelating agent comprises a plurality of substituted acetic acid groups.

20 6. A composition according to claim 5, characterised in that the chelating agent is a EDTA, DTPA, HEDTA, NTA, or a combination thereof.

7. A composition according to any one of claims 3 - 6, characterised in that the silica is colloidal.
25

8. A method for chemical mechanical polishing of a semiconductor substrate, characterised in that a composition according to any of claims 3 - 7 is used to polish said substrate.

30 9. A method according to claim 8, characterised in that the method is a chemical mechanical planarization method.

10. A method according to claim 8 or 9, characterised in that said semiconductor is Si, GaAs, InP, or Ge

INTERNATIONAL SEARCH REPORT

Int Application No
PCT/SE 98/02370

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09K3/14 C09G1/02 H01L21/321

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 8851 Derwent Publications Ltd., London, GB; Class A97, AN 88-363748 XP002100340 & JP 63 272460 A (MITSUBISHI MONSANTO KK) , 9 November 1988 see abstract	1,3-10
X	US 4 954 142 A (CARR JEFFREY W ET AL) 4 September 1990 see column 3, line 31 - line 66; examples 1-4	1,3-10
X	US 4 462 188 A (PAYNE CHARLES C) 31 July 1984 see table 1	1,3,4, 7-10
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 April 1999

Date of mailing of the international search report

28/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Shade, M

INTERNATIONAL SEARCH REPORT

Int Application No
PCT/SE 98/02370

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 520 109 A (NALCO CHEMICAL CO) 30 December 1992 see page 6, line 1 - line 15 see page 7, line 35 - line 49 ---	1-4,7-10
X	US 5 376 222 A (MIYAJIMA MOTOSHU ET AL) 27 December 1994 see column 5, line 3 - line 9; example 3 ---	1-4,7-10
X	EP 0 392 364 A (TOKYO SHIBAURA ELECTRIC CO) 17 October 1990 see page 4, column 5, line 7 - line 24 ---	1-3,8,10
X	EP 0 774 777 A (IBM) 21 May 1997 see page 3, column 4, line 4 - line 18 ---	1-3,8-10
X	US 3 715 842 A (DUPREE P ET AL) 13 February 1973 cited in the application see column 3, line 5 - line 27; example 1 -----	1-3,8-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

In Application No

PCT/SE 98/02370

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4954142 A	04-09-1990	CA 2011709 A,C DE 69024263 D DE 69024263 T EP 0401147 A ES 2080818 T JP 1969537 C JP 2278822 A JP 6103681 B US 5084071 A	07-09-1990 01-02-1996 11-07-1996 05-12-1990 16-02-1996 18-09-1995 15-11-1990 14-12-1994 28-01-1992
US 4462188 A	31-07-1984	JP 1372926 C JP 58225177 A JP 61038954 B	07-04-1987 27-12-1983 01-09-1986
EP 0520109 A	30-12-1992	AT 120433 T DE 69108546 D DE 69108546 T FI 914594 A US 5230833 A	15-04-1995 04-05-1995 30-11-1995 29-11-1992 27-07-1993
US 5376222 A	27-12-1994	JP 5062953 A JP 5067600 A	12-03-1993 19-03-1993
EP 0392364 A	17-10-1990	JP 2268425 A JP 2726488 B DE 69023685 D DE 69023685 T US 5188987 A	02-11-1990 11-03-1998 04-01-1996 09-05-1996 23-02-1993
EP 0774777 A	21-05-1997	US 5885899 A JP 9186237 A	23-03-1999 15-07-1997
US 3715842 A	13-02-1973	NONE	